

High Density Polyethylene HA7260

Description:

HA7260 is a high-density polyethylene, developed for the injection molding, easy to process and with high productivity.

This resin has a good melt flow with high rigidity and hardness. Its narrow molar mass distribution results in a low tendency to warpage.

Application:

Pails & basins, Toys, Lids, Thin-walled parts and Housewares

Process:

Injection Molding

Control Properties:

	ASTM Methods	Units	Values
Melt Flow Rate (190/2.16)	D 1238	g/10 min	20
Density	D 792	g/cm ³	0.955

Typical Properties:

Plaque Properties^a

	ASTM Methods	Units	Values
Tensile Strength at Yield	D 638	MPa	29
Tensile Elongation at Yield	D 638	%	7,2
Flexural Modulus – 1% Secant	D 790	MPa	1350
Shore D Hardness	D 2240	-	64
Notched Izod Impact Strength	D 256	J/m	25
Environmental Stress Cracking Resistance ^b	D 1693	h/F50	< 4
Vicat Softening Temperature at 10 N	D 1525	°C	124
Deflection Temperature under Load at 0.455 MPa	D 648	٥C	74

(a) Test specimens prepared from compression molded sheet made according to ASTM D 4703.

(b) Compression molded 2 mm thickness, 0.3 mm notched-plaques; 100% Igepal; 50°C

Final Remarks:

This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA - Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted

2. values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product. 3.

In some applications, Braskem has developed tailor-made resins to reach specific requirements. 4.

In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25087-34-7. 5.

The mentioned values in this report can be changed at any moment without Braskem previous communication.

6. 7. Braskem does not recommend this grade for packages, parts or any kind of product manufacture that will be used for storage or contact with solution that will have internal contact with human body. The content of this Data Sheet replaces previous revisions published for this product.

8.