



# High Density Polyethylene SGF4950HS

## Description:

SGF4950HS is a High Density Polyethylene, copolymer, offering an outstanding combination of good processability and excellent stress cracking resistance (ESCR). It is recommended for the production of containers, flasks and bottles up to 30 liters for the transport of chemical products.

The minimum biobased content of this grade is 95%, determined according to ASTM D6866.

### Application:

Suggested uses include: Canisters from 2 to 20L for chemical products; Flasks for concentrated detergent. Others applications: Reservoir for wind shield wiper and air ducts.

#### Process:

Blow Molding.

#### **Control Properties:**

|                               | ASTM Method | Units             | Values |
|-------------------------------|-------------|-------------------|--------|
| Melt Flow Rate (190°C/2.16kg) | D 1238      | g/10 min          | 0.21   |
| Melt Flow Rate (190°C/21.6kg) | D 1238      | g/10 min          | 20     |
| Density                       | D 792       | g/cm <sup>3</sup> | 0.951  |

# **Typical Properties:**

Plaque Properties<sup>a</sup>

|   | ASTM Method | Units | Values |
|---|-------------|-------|--------|
| Tensile Strength at Break                             | D 638       | MPa   | 35     |
| Flexural Modulus – 1% Secant                          | D 790       | MPa   | 1100   |
| Izod Impact Strength                                  | D 256       | J/m   | 175    |
| Environmental Stress Cracking Resistance <sup>b</sup> | D 1693      | h/F50 | 150    |
| Environmental Stress Cracking Resistance <sup>c</sup> | D 1693      | h/F50 | 1000   |
| Deflection Temperature under Load at 0.455 MPa        | D 648       | ٥C    | 70     |

(a) Test specimens prepared from compression molded sheet made according to ASTM D 4703.

(b) Compression molded 2 mm thickness, 0.3 mm notched-plagues. 10% Igepal. 50°C.

(c) Compression molded 2 mm thickness, 0.3 mm notched-plaques. 100% Igepal. 50°C.

# **Recommended Processing Conditions:**

#### **Temperature Profile:**

- Feeding Zone: 180 °C
- Barrel: 180, 185 and 190 °C
- Die: 185 °C •

#### **Final Remarks:**

- This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA
- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product. 2.
- In some applications, Braskem has developed tailor-made resins to reach specific requirements.
- In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance. 5.
- For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25087-34-7. The mentioned values in this report can be changed at any moment without Braskem previous communication. 6.
- Braskem does not recommend this grade for packages, parts or any kind of product manufacture that will be used for storage or contact with solution that will have internal contact with human body.
- The content of this Data Sheet replaces previous revisions published for this product. 8.
- 9. This resin does not contain the substance Bisphenol A (BPA, CAS # No. 80-05-7) in its composition.